



PAVSEEL®

For in-situ binding of jointing sand in block paving.

Anglo Pavseel Solvent Free has proved to be the ultimate answer to the problems associated with stabilising the essential jointing sand and helping to protect the integrity of block paving in some of the world's most demanding applications.

- **Reduces maintenance costs**
Resists jointing sand removal
- **Withstands vacuum cleaning**
Strengthens pavements
- **Inhibits water/fuel penetration**
Inhibits weed growth
- **Long performance life**
Easy to apply
- **Stable under normal UV radiation**

Anglo Pavseel Solvent Free is ideal for use on footpaths, pedestrian precincts, domestic driveways, office car parks, retail parks and highways.



PROFESSIONAL QUALITY

PRODUCT INFORMATION

ANGLO PAVSEEL®

APPEARANCE

Opaque on application which clears once cured. Application will result in a slight darkening of the blocks. We recommend inconspicuous testing on colour-crucial areas.

AVAILABILITY

Available in 5 litre and 25 litre containers.

COVERAGE

Typical coverage is approximately 10m² per 5 litres, depending on the porosity of the pavers, block size and joint width.

STORAGE

Keep in a cool place (between 10°C and 30°C). Do not allow to freeze.

Surface Preparation

Surfaces to be treated must be dry, free from grease, oil, dirt and previous coatings. Joints should be filled or topped up to the bottom of the chamfer with clean, dry compacted sand of the correct specification.

APPLICATION

Ground temperatures should be between 10°C and 30°C. Apply only when the blocks, jointing sand and bedding sand are dry and when rain is not expected for at least 24 hours. Only one application is required. Pour directly from the container or apply with a watering can fitted with a rose. Low pressure spray systems can also be used. Do not flush out the jointing sand. Work in areas of approximately 5m², distributing the liquid evenly with a foam rubber squeegee. Ensure that the joints are completely filled with liquid and that the joints and pavers have absorbed as much solution as they can. Use the squeegee to remove all unabsorbed liquid from the surface of the pavers.

Please Note: the product must not be allowed to pond on the surface of the pavers or create a surface film. Any unabsorbed material must be pushed away using the squeegee. Dry conditions at the time of application are important since damp or rain in contact with uncured Anglo Pavseel can cause the product to dry with a whitish 'bloom'. This effect will be exaggerated if any surplus of solution is not removed from the blocks with the squeegee at the time of application.

CURING TIME

Surfaces treated with Anglo Pavseel Solvent Free can normally be re-opened to foot traffic within 12 - 24 hours. Protect from rain and frost while curing. A warm dry wind will speed curing time.

LIMITATIONS

Only suitable for application to bare, unsealed block pavers.

SAFETY

Anglo Pavseel must not be flushed down drains, storm drains or allowed to enter open water courses. All product labels provide general safety information. Material Safety Data Sheets are available. Food products must be removed from the area during application and cure.